

## <u>Fujian Anyuan (Antai) Rubber Technology Co., Ltd</u> <u>Shenzhen Mingpai Technology Co., Ltd</u>

# C5 Petroleum Resin Technical Instructions(TDS)

Active ingredients	C5 Petroleum Resin	Other ingredients	None
--------------------	--------------------	-------------------	------

### **Product introduction**

C5 petroleum resin is a kind of thermoplastic resin, which is made from C5 fraction, by-product of ethylene cracking unit. This product has good water resistance/acid and alkali resistance/water resistance and other characteristics. In the rubber industry, it can increase viscosity and plasticity, reduce frost and improve skid resistance. In the high filling compound, the adhesive filler can reduce the attenuation of the phsical properties of the compound.

#### **Product index**

ltems	softening point	color code	acid value	ash content	bromine value
Unit	°C		mg/g	%	g/100g
Index	90-110	44259.00	0.2-0.4	≥13.0	20-50

## Usage method

In order to ensure its uniform dispersion, the internal mixer temperature should	
not be lower than 100 °C	
Adjustment is required before final prodcut testing	
Recommended dosage: 1phr- 5phr	

## Package specification/ shelf life

25kg/bag

Twelve months from the date of production. If the storage is expired, it can still be used after re inspection

## **Attention points**

1. This product is flammable, avoid contact with fire	Flammability
2. Keep away from non-polar oil to prevent its melting and deterioration	
3. Store in a well ventilated and dry place	inflammable

Company Name	Fujian Anyuan Rubber Technology Co., Ltd		
Address	No. 22, Jiulongshan Industrial Zone, Hongku, Hanjiang Town, Shishi City, Fuji		
Phone	0595-85151198	Website	www.fjayxj.com